## **ANUCHROME – LEMON CHROME L-24**

ANUCHROME Lemon Chrome L-24 is a monoclinic Lead Chromate material, also known as Pre-Darkened Lemon Chrome. This pigment is highly stabilized and is of very good light fastness and exterior durability.

Therefore, it is suitable for high grade automotive coatings meant for refinishing purposes. It possesses good resistance to acidic environment.

## **TECHNICAL DATA**

Colour Index No.	77603					
Colour Index Pigment No.	Y-34					
Oil Absorption	16-21					
Specific Gravity	4.9-6.0					
Bulk Density g/cc	0.76					
BLEEDING IN (1-Poor 5-Excellent)						
Water	5					
5% Caustic Soda	3					
5% Hydrochloric Acid	3					
Linseed Oil	5 5					
Ethanol	5					
Ethyl Acetate	5					
Xylene	5					
n-Butanol	5					
Methyl Ethyl Ketone	5 5 5 5					
Mineral Turpentine	5					
Cellosolve	5					
Dioctyl Phthalate	5					
RESISTANCE TO HEAT						
120°C / 30 min.	SB					
150°C / 20 min.	SB					
180°C / 10 min.	USB					
210°C / 10 min.	USB					
RESISTANCE TO LIGHT						
Full Tone	7					
Tint Tone (1:10)	7					
RESISTANCE TO						
Acid	G					
Alkali	Р					
APPLICATIONS						
Paints	*					
Printing Inks	*					
Rubber						
Leather Pastes	*					
Linoleum	*					
PVC Leather Cloth	*					
Paper Coating	*					

Chalk / Crayons	
Plastics	*

## **LEGEND**

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E - EXCELLENT
Y – YELLOW	SCALE (1-5)	SB: STABLE	SCALE (1-8)	*:RECOMMENDED/	<b>VG</b> – VERY GOOD
R - RED	5:NO BLEED	USB: UNSTABLE	1 – POOR	MAYBE USED	<b>G</b> -GOOD
W – WHITE	1:CONSIDERA	BLE BLEED	8 – EXCELLENT	F - FAIR	
					P - POOR