

ANUCHROME – MIDDLE CHROME M-13

ANUCHROME M-13 is a general purpose Middle Chrome used in the manufacture of Synthetic Enamels and Printing Inks. This pigment is stabilized and offers good fastness to light and weather.

TECHNICAL DATA

Colour Index No.	77603
Colour Index Pigment No.	Y-34
Oil Absorption	15-20
Specific Gravity	5.1-6.0
Bulk Density g/cc	0.87
BLEEDING IN	
Water	5
5% Caustic Soda	3
5% Hydrochloric Acid	3
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocetyl Phthalate	5
RESISTANCE TO HEAT	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	SB
210°C / 10 min.	USB
RESISTANCE TO LIGHT	
Full Tone	7
Tint Tone (1:10)	7
RESISTANCE TO	
Acid	G
Alkali	P
APPLICATIONS	
Paints	*
Printing Inks	*
Rubber	
Leather Pastes	*
Linoleum	*
PVC Leather Cloth	*
Paper Coating	*

Chalk / Crayons	
Plastics	*

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E – EXCELLENT
Y – YELLOW GOOD	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/ MAYBE USED	VG – VERY
R – RED W – WHITE	5:NO BLEED 1:CONSIDERABLE BLEED	USB : UNSTABLE	1 – POOR 8 – EXCELLENT		G – GOOD F – FAIR P – POOR