

ANUCHROME – MIDDLE CHROME M-14

This Pigment is highly stabilized, and is a pre-darkened Chrome, providing excellent light fastness and exterior durability. Therefore, this pigment is most suitable for high quality coatings meant for Auto refinishing purposes. It possesses good resistance to acidic environment. Therefore this pigment is strongly recommended for Paints where better Light Fastness is required.

TECHNICAL DATA

Colour Index No.	77603
Colour Index Pigment No.	Y-34
Oil Absorption	15-20
Specific Gravity	5.1-6.0
Bulk Density g/cc	0.62
BLEEDING IN	
Water	5
5% Caustic Soda	3
5% Hydrochloric Acid	3
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocetyl Phthalate	5
RESISTANCE TO HEAT	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	USB
210°C / 10 min.	USB
RESISTANCE TO LIGHT	
Full Tone	8
Tint Tone (1:10)	8
RESISTANCE TO	
Acid	G
Alkali	P
APPLICATIONS	
Paints	*
Printing Inks	*
Rubber	
Leather Pastes	*
Linoleum	*
PVC Leather Cloth	*
Paper Coating	*
Chalk / Crayons	

Plastics	*
----------	---

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E – EXCELLENT
Y – YELLOW GOOD	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/	VG – VERY
R – RED	5:NO BLEED	USB : UNSTABLE	1 – POOR	MAYBE USED	G – GOOD
W – WHITE	1:CONSIDERABLE BLEED		8 – EXCELLENT		F – FAIR
					P – POOR