

ANUCHROME – SCARLET CHROME S-46

ANUTHERM RED S-46 is a Molybdate Orange Pigment and is also popularly known as Scarlet Chrome. This is an economical variety in Scarlet Chromes. It is a stabilized product and offers fairly good resistance to light and weather.

TECHNICAL DATA

Colour Index No.	77605
Colour Index Pigment No.	R-104
Oil Absorption	14-20
Specific Gravity	5.2-6.0
Bulk Density g/cc	1.25
BLEEDING IN (1-Poor 5-Excellent)	
Water	5
5% Caustic Soda	3
5% Hydrochloric Acid	3
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocetyl Phthalate	5
RESISTANCE TO HEAT	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	SB
210°C / 10 min.	USB
RESISTANCE TO LIGHT	
Full Tone	5
Tint Tone (1:10)	6
RESISTANCE TO	
Acid	F
Alkali	P
APPLICATIONS	
Paints	*
Printing Inks	*
Rubber	
Leather Pastes	*
Linoleum	*
PVC Leather Cloth	*
Paper Coating	*
Chalk / Crayons	

Plastics	*
----------	---

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	
Y – YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/	E – EXCELLENT
R – RED	5:NO BLEED	USB : UNSTABLE	1 – POOR	MAYBE USED	VG – VERY GOOD
W – WHITE	1:CONSIDERABLE BLEED		8 – EXCELLENT		G – GOOD
					F – FAIR
					P – POOR