

## ANUCHROME – SCARLET CHROME S-47

ANUCHROME S-47 is a Molybdate Orange. It is a pre-darkened quality with yellower tone in our Scarlet Chrome range of Pigments. This is a highly stabilized pigment and offers very good fastness to light and weathering. This product, due to its excellent light fastness characteristics is strongly recommended for automotive coatings meant for refinishing purpose and also for Synthetic Enamels where better light fastness is required.

### TECHNICAL DATA

Colour Index No.	77605
Colour Index Pigment No.	R-104
Oil Absorption	14-20
Specific Gravity	5.2-6.0
Bulk Density g/cc	0.93
<b>BLEEDING IN (1-Poor 5-Excellent)</b>	
Water	5
5% Caustic Soda	3
5% Hydrochloric Acid	3
Linseed Oil	5
Ethanol	5
Ethyl Acetate	5
Xylene	5
n-Butanol	5
Methyl Ethyl Ketone	5
Mineral Turpentine	5
Cellosolve	5
Diocetyl Phthalate	5
<b>RESISTANCE TO HEAT</b>	
120°C / 30 min.	SB
150°C / 20 min.	SB
180°C / 10 min.	USB
210°C / 10 min.	USB
<b>RESISTANCE TO LIGHT</b>	
Full Tone	8
Tint Tone (1:10)	8
<b>RESISTANCE TO</b>	
Acid	F
Alkali	P
<b>APPLICATIONS</b>	
Paints	*
Printing Inks	*
Rubber	
Leather Pastes	*
Linoleum	*
PVC Leather Cloth	*
Paper Coating	
Chalk / Crayons	

Plastics	*
----------	---

**LEGEND**

<b>COLOUR</b>	<b>BLEEDING</b>	<b>HEAT STABILITY</b>	<b>LIGHTFASTNESS</b>	<b>APPLICATIONS</b>	
Y – YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/	<b>E</b> – EXCELLENT
R – RED	5:NO BLEED	USB : UNSTABLE	1 – POOR	MAYBE USED	<b>VG</b> – VERY GOOD
W – WHITE	1:CONSIDERABLE BLEED		8 – EXCELLENT		<b>G</b> – GOOD
					<b>F</b> – FAIR
					<b>P</b> – POOR