



+9111-41545575, 45070101

Anuradha Enterprises Pvt. Ltd.

Unit 126, Ring Road Mall, Mangalam Place, Sector-3

Rohini, New Delhi-110085, INDIA

Email: sales@anuradha.co.in; Website: www.anuradha.co.in

CIN NO – U00000DL2001PTC110116

Modified Phenolic Resin 701

Description:

701 is Rosin modified Oil soluble Phenolic Resin.

Specifications:

Melting Point	:	125-135°C
Viscosity (50% in MTO at 30°C)	:	160-180 Seconds
Maximum Acid Value	:	25.0 mg KOH/gm
Maximum Colour	:	3 – 3 ½ PRS / 12 Gardner

Solubility:

701 is completely soluble in Aromatic Hydrocarbon, Esters and Varnishes Oils.

Compatibility:

701 is compatible with Long, Medium Oil and Rosinated Alkyds and Vegetable Oils.

Uses:

Letter Press and Offset Inks.

.....
(The recommendations in this bulletin are made without guarantee since
the conditions of use are beyond our control. Users should make their own
tests depending on machinery available and desired properties.)

Serving the Surface Coating Industry