

SYNOCRYL® 874X-45

ARKEMA COATING RESINS

Product Application details

SYNOCRYL® 874X-45 is a thermoplastic acrylic copolymer possessing the excellent color, gloss retention and good adhesion to plastics, metals, wood and fabrics are the properties of resin.

Performance

Benefits

- Excellent color retention at elevated temperature
- Excellent soap and detergent resistance
- Excellent adhesion on bare metal
- Good compatibility with broad range of resin and plasticizers

Polymer Type

- Solvent borne Acrylic

Sales

Specifications

Non-volatile content, % (ISO 3251, 1gm, 1h, 125°C)	43-47
Viscosity in Poise at 25°C, Brookfield Viscometer (ISO 3219)	10 - 15
Colour, Gardner scale (ISO 4630)	Max 1
Acid value, mg KOH/g (ISO 2114)	Max 10

Other

Characteristics

Volatile Aromatic solvent	Xylene
Density at 25°C, g/cm ³ (ISO 2811)	0.97

RECOMMENDATIONS FOR USE

Water white films are deposited from the resin, and clear or pigmented films possess fast air dry times and are resistant to soaps and detergents. The films are also resistant to degradation when exposed to heat or edging. The versatility of SYNOCRYL® 874X-45 enables it to be used in variety of finishes either as the sole vehicle in clear or pigmented coatings for various plastics, metal, wood and fabrics or as a modifying resin to improve the drying time, durability and resistance properties of other coating systems

Formulating Guidelines

SYNOCRYL® 874X-45 is soluble in a range of aromatic hydrocarbons, esters and ketones. The resin has limited solubility in aliphatic hydrocarbons and alcohols.

SYNOCRYL® 874X-45 is compatible with a range of cellulose esters, vinyl resins and chlorinated rubber.

SYNOCRYL®

SYNOCURE® 874X-45 should only be used in applications consistent with the above recommendations.

Proposals to use the resin in other ways should be discussed with Arkema before any action is taken.

Product & Safety

Please refer to the corresponding Safety Data Sheet

Storage & Handling

SYNOCURE® 874X-45 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

Under the above mentioned storage conditions the shelf life of the resin will be 12 months from the date of manufacturing.

January 2023

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications. Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Chemicals India Pvt Ltd
D43 (1), Trans Thane Creek, MIDC Industrial Area,
Shiravane, Nerul, Navi Mumbai 400706, India
Telephone: +91 22 6737 7100
Fax: +91 22 2768 7998

ARKEMA